



2931 Exon Ave. ■ Cincinnati, Ohio 45241
(513) 733-0883 ■ FAX (513) 733-1096

BUNA-N 60 DURO "A"

| | |
|-----------------------------|-------------------------|
| NRC COMPUTER CODE: | BUNA 60 |
| ASTM-D-2000 CLASSIFICATION: | BF 609 |
| CHEMICAL DEFINITION: | BUTADIENE ACRYLONITRILE |
| DUROMETER (SHORE A): | 60 +/-5 |
| TENSILE STRENGTH: | 900 PSI MIN |
| ELONGATION: | 200% MIN |
| LOW TEMPERATURE: | -20° F |
| HIGH TEMPERATURE: | 180° F |
| ABRASION RESISTANCE: | GOOD |
| OIL RESISTANCE: | EXCELLENT |
| SUNLIGHT AGING: | POOR |

GENERALLY RESISTANT TO:

MOST HYDROCARBONS, FATS, OILS, GREASES, HYDRAULIC FLUIDS, CHEMICALS, AND SOLVENTS.

GENERALLY AFFECTED BY:

OZONE, KETONES, ESTERS, ALDEHYDES, NITRO AND CHLORINATED HYDROCARBONS, POLAR SOLVENTS, MEK.

This information is furnished as a guide for selecting materials. NRC disclaims liability for results or use of this information. It is the customer's responsibility to obtain and test samples when determining suitability of material for a particular application.