



2931 Exon Ave. ■ Cincinnati, Ohio 45241  
(513) 733-0883 ■ FAX (513) 733-1096

## **BUTYL 60 DURO**

NRC COMPUTER CODE:	BUTYL 60
ASTM-D-2000 CLASSIFICATION:	AA
CHEMICAL DEFINITION:	CHLORO-ISOBUTYLENE ISOPRENE
DUROMETER (SHORE A):	60 +/- 5
TENSILE STRENGTH:	1000 PSI MIN
ELONGATION:	300% MIN
LOW TEMPERATURE:	-20°F
HIGH TEMPERATURE:	200°F
ABRASION RESISTANCE:	GOOD
OIL RESISTANCE:	POOR
SUNLIGHT AGING:	VERY GOOD

### GENERALLY RESISTANT TO:

ANIMAL AND VEGETABLE: OILS, FATS, GREASES, AIR, WATER, GAS, MANY  
OXIDIZING CHEMICALS AND OZONE.

### GENERALLY AFFECTED BY:

OILS, SOLVENTS, AROMATIC HYDROCARBONS.

This information is furnished as a guide for selecting materials. NRC disclaims liability for results or use of this information. It is the customer's responsibility to obtain and test samples when determining suitability of material for a particular application.