



2931 Exon Ave. ■ Cincinnati, Ohio 45241
(513) 733-0883 ■ FAX (513) 733-1096

EPDM 60 DURO "A"

NRC COMPUTER CODE:	EPDM 60
ASTM-D-2000 CLASSIFICATION:	2BA 608
CHEMICAL DEFINITION:	ETHYLENE PROPYLENE POLYMER
DUROMETER (SHORE A):	60 +/-5
TENSILE STRENGTH:	800 PSI MIN
ELONGATION:	250% MIN
LOW TEMPERATURE:	-40° F
HIGH TEMPERATURE:	212° F
ABRASION RESISTANCE:	GOOD
OIL RESISTANCE:	POOR
SUNLIGHT AGING:	OUTSTANDING

GENERALLY RESISTANT TO:

VEGETABLE AND ANIMAL FATS, OILS, OZONE, MANY STRONG AND OXIDIZING CHEMICALS, KETONES, AND ALCOHOLS.

GENERALLY AFFECTED BY:

MINERAL OILS, SOLVENTS, AROMATIC HYDROCARBONS.

This information is furnished as a guide for selecting materials. NRC disclaims liability for results or use of this information. It is the customer's responsibility to obtain and test samples when determining suitability of material for a particular application.