



2931 Exon Ave. ■ Cincinnati, Ohio 45241  
(513) 733-0883 ■ FAX (513) 733-1096

## **NEOPRENE 60 SHEET RUBBER**

NRC COMPUTER CODE:	NEO 60
ASTM-D-2000 CLASSIFICATION:	BC 608
CHEMICAL DEFINITION:	POLY-CHLOROPRENE
DUROMETER (SHORE A):	60 +/- 5
TENSILE STRENGTH:	800 PSI MIN
ELONGATION:	250% MIN
LOW TEMPERATURE:	-20°F
HIGH TEMPERATURE:	170°F
ABRASION RESISTANCE:	EXCELLENT
OIL RESISTANCE:	GOOD
SUNLIGHT AGING:	GOOD

### GENERALLY RESISTANT TO:

MODERATE ACIDS AND CHEMICALS, OZONE, OILS, FATS, AND MANY SOLVENTS, OILY ABRASIVE APPLICATIONS.

### GENERALLY AFFECTED BY:

OXIDIZING ACIDS, ESTERS, AND KETONES, AROMATIC, CHLORINATED AND NITRO HYDROCARBONS.

This information is furnished as a guide for selecting materials. NRC disclaims liability for results or use of this information. It is the customer's responsibility to obtain and test samples when determining suitability of material for a particular application.