



2931 Exon Ave. ■ Cincinnati, Ohio 45241
(513) 733-0883 ■ FAX (513) 733-1096

NEOPRENE 80 SHEET RUBBER

NRC COMPUTER CODE:	NEO 80
ASTM-D-2000 CLASSIFICATION:	BC 810
CHEMICAL DEFINITION:	POLY-CHLOROPRENE
DUROMETER (SHORE A):	80 +/- 5
TENSILE STRENGTH:	1000 PSI MIN
ELONGATION:	100% MIN
LOW TEMPERATURE:	-20°F
HIGH TEMPERATURE:	170°F
ABRASION RESISTANCE:	EXCELLENT
OIL RESISTANCE:	GOOD
SUNLIGHT AGING:	GOOD

GENERALLY RESISTANT TO:

MODERATE ACIDS AND CHEMICALS, OZONE, OILS, FATS, AND MANY SOLVENTS, OILY ABRASIVE APPLICATIONS.

GENERALLY AFFECTED BY:

OXIDIZING ACIDS, ESTERS, AND KETONES, AROMATIC, CHLORINATED AND NITRO HYDROCARBONS.

This information is furnished as a guide for selecting materials. NRC disclaims liability for results or use of this information. It is the customer's responsibility to obtain and test samples when determining suitability of material for a particular application.