



2931 Exon Ave. ■ Cincinnati, Ohio 45241  
(513) 733-0883 ■ FAX (513) 733-1096

## **RED REINFORCED SILICONE**

NRC COMPUTER CODE:	FHT-1500R
SPECIFICATION:	AMS-3320
DUROMETER (SHORE A):	70 +/-10
BREAKING STRENGTH (PPI):	300 MIN
COMPRESSION SET:	35% MAX
LOW TEMPERATURE:	-80° F
HIGH TEMPERATURE:	450° F
FABRIC:	FIBERGLASS

This information is furnished as a guide for selecting materials. NRC disclaims liability for results or use of this information. It is the customer's responsibility to obtain and test samples when determining suitability of material for a particular application.

7/2010