



2931 Exon Ave. ■ Cincinnati, Ohio 45241
(513) 733-0883 ■ FAX (513) 733-1096

RED SILICONE 60 DURO "A"

NRC COMPUTER CODE:	SIL-R-60
MILITARY SPECIFICATION:	ZZ-R-765D CL 2A 2B GR 60
CHEMICAL DEFINITION:	POLY SILOXANE
DUROMETER (SHORE A):	60 +/- 5
TENSILE STRENGTH:	900 PSI MIN
ELONGATION:	400% MIN
LOW TEMPERATURE:	-75°F
HIGH TEMPERATURE:	400°F
ABRASION RESISTANCE:	POOR
OIL RESISTANCE:	FAIR
SUNLIGHT AGING:	EXCELLENT

GENERALLY RESISTANT TO:

MODERATE OR OXIDIZING CHEMICALS, OZONE, CONCENTRATED SODIUM HYDROXIDE.

GENERALLY AFFECTED BY:

MANY SOLVENTS, OILS, CONCENTRATED ACIDS, SULFURS.

This information is furnished as a guide for selecting materials. NRC disclaims liability for results or use of this information. It is the customer's responsibility to obtain and test samples when determining suitability of material for a particular application.