



2931 Exon Ave. ■ Cincinnati, Ohio 45241
(513) 733-0883 ■ FAX (513) 733-1096

VITON 75 DURO "A"

NRC COMPUTER CODE:	VITON 75
ASTM-D-2000 CLASSIFICATION:	HK-710
CHEMICAL DEFINITION:	FLUORINATED HYDROCARBON
DUROMETER (SHORE A):	75 +/-5
TENSILE STRENGTH:	1000 PSI MIN
ELONGATION:	750% MIN
LOW TEMPERATURE:	-20° F
HIGH TEMPERATURE:	400° F
ABRASION RESISTANCE:	GOOD
OIL RESISTANCE:	EXCELLENT
SUNLIGHT AGING:	OUTSTANDING

GENERALLY RESISTANT TO:

ALL AROMATIC, ALIPHATIC AND HALOGENATED HYDROCARBONS, MANY ACIDS,
ANIMAL AND VEGETABLE OILS.

GENERALLY AFFECTED BY:

KETONES, ESTERS, AND NITRO CONTAINING COMPOUNDS.

This information is furnished as a guide for selecting materials. NRC disclaims liability for results or use of this information. It is the customer's responsibility to obtain and test samples when determining suitability of material for a particular application.