



2931 Exon Ave. ■ Cincinnati, Ohio 45241
(513) 733-0883 ■ FAX (513) 733-1096

OPEN CELL SPONGE OC-SP 10

COLOR:	BLACK
COMPOUND:	NATURAL RUBBER
ASTM D-1056-67:	RO-11
SAE-18R:	RO-18
MIL-C 3133R:	RO-3
MIL-STD-670A:	RO-3
DENSITY:	30-40 PCF
ELONGATION:	200%
TENSILE STRENGTH:	75 PSI MIN
25% COMPRESSION DEFLECTION:	2-5 PSI
COMPRESSION SET (50% 22 HRS @ 158°F):	15% MAX
WEATHERING AND OZONE RESISTANCE:	POOR
LOW TEMPERATURE:	-40°F
HIGH TEMPERATURE CONTINUOUS:	150°F MAX
HIGH TEMPERATURE INTERMITTENT:	200°F MAXs

This information is furnished as a guide for selecting materials. NRC disclaims liability for results or use of this information. It is the customer's responsibility to obtain and test samples when determining suitability of material for a particular application.