



2931 Exon Ave. ■ Cincinnati, Ohio 45241  
(513) 733-0883 ■ FAX (513) 733-1096

## **WHITE FDA SPONGE**

COMPOUND:	SBR
25% COMPRESSION DEFLECTION:	5-13 PSI
DUROMETER (SHORE 00):	40-65
DENSITY:	9-15 PCF
WATER ABSORPTION:	5% MAX
LOW TEMPERATURE:	-70°F
HIGH TEMPERATURE CONTINUOUS:	180°F
HEAT AGING LINEAL SHRINKAGE:	10%
TENSILE STRENGTH:	50 PSI MIN
ELONGATION:	100% MIN

\*PRODUCED FROM FDA APPROVED INGREDIENTS.

This information is furnished as a guide for selecting materials. NRC disclaims liability for results or use of this information. It is the customer's responsibility to obtain and test samples when determining suitability of material for a particular application.

7/2010