



2931 Exon Ave. ■ Cincinnati, Ohio 45241
(513) 733-0883 ■ FAX (513) 733-1096

SPONGE CORD

NRC COMPUTER CALL OUT:	N6E SPC-0616
POLYMER BASE:	NEOPRENE BLEND
ASTM-D-1056-68:	SCE-41-42
25% COMPRESSION DEFLECTION:	3-8 PSI
DUROMETER (SHORE 00):	30-55
DENSITY:	6-10 LBS./CU. FT.
TENSILE STRENGTH:	40 PSI
ELONGATION:	150%
LOW TEMPERATURE:	-40° F
HIGH TEMPERATURE:	200° F

This information is furnished as a guide for selecting materials. NRC disclaims liability for results or use of this information. It is the customer's responsibility to obtain and test samples when determining suitability of material for a particular application.