



2931 Exon Ave. ■ Cincinnati, Ohio 45241
(513) 733-0883 ■ FAX (513) 733-1096

SILICONE SPONGE

NRC-SIL-SP

COMPOUND:	SILICONE
DENSITY:	22 PCF
25% COMPRESSION DEFLECTION:	9 PSI
COMPRESSION SET:	< 5%
TENSILE STRENGTH:	45 PSI
ELONGATION:	80%
STRUCTURE:	OPEN/CLOSED
WATER ABSORPTION:	5% MAX
FLAME RESISTANCE:	
UL94 V-O	PASS
UL94 HF-1	PASS
FMVSS 302	PASS
FAR 25.853	PASS
HIGH TEMPERATURE-CONSTANT:	392°F
LOW TEMPERATURE:	-67°F

***NOTE- UL LISTED**

This information is furnished as a guide for selecting materials. NRC disclaims liability for results or use of this information. It is the customer's responsibility to obtain and test samples when determining suitability of material for a particular application.

7/2010